

DGC 5412

Is a sprayable dual-component metallic reinforced high-performance liquid polymer composite for surface repairs, corrosion prevention, and protection against erosion abrasion and chemical attack, DGC5412 was designed with special metallic fillers to provide an elevated hardness and easy machining, allowing repairs that require a finish with close tolerances.

MAXIMIZING YOUR BENEFITS

SPRAYABLE

A simpler and faster way to protect your asset

METALLIC FILLERS BLEND

When low close tolerance machining is required

100% SOLIDS; NO VOCS

Making it a great choice for any environmentally friendly project

EASY TO MIX AND APPLY

Requires no special tools or skills, perfect for applications by spray

MAXIMIZING YOUR APPLICATIONS

- Cyclones
- Exhausters
- Pipe elbows
- Wear plates
- Slurry pumps
- Pump casings
- Hydraulic pistons
- Repair of damaged shafts
- Turbo separators
- Structural repairs

CURING TIMES (25°C)

Dry-to-touch	2 hrs
No loading or immersion	4 hrs
Machining or light loading	6 hrs
Full mechanical load	24 hrs
Full chemical	270 hrs
Dry Film Thickness	250 µm

PROPERTIES

Adhesion ASTM D4541	30 Mpa >4300 psi
Compressive Strength ASTM D695	90 Mpa >13000 psi
Hardness (Shore D) ASTM D2240 (24h)	78
Hardness (Shore D) ASTM D2240 (72h)	83
Tensile Strength ASTM D638	33 Mpa >4700 psi
Flexural Strength ASTM D790	122 Mpa >17700 psi
Impact Resistance ASTM D256	6.0 kJ/m ²
Temperature Resistance ASTM D 3418	100 °C 212 °F
Heat Resistance	200 °C 392 °F

THEORETICAL COVERAGE @ 250 µm

WINDOW RECOAT

1 kg covers	3,08 m ²	Minimum	2 hrs
5 kg covers	15,40 m ²	Maximum	4 hrs

PACKING

DATA

DGC 5412.01	1 kg	Ratio Volume	4:1
DGC 5412.05	5 kg	Ratio Weight	9:1
DGC 5412.20	20 kg	Working time	20 mins
Shelf Life	24 months	Density A + B	1.30

ZAMBIA
 DICKINSON COPPERBELT SERVICES LTD
 DGC WORKFORCE SOLUTIONS

T +260 76 183 2470
 T +260 96 552 4350
 T +260 96 146 6000
 E contactus@dgc-africa.com

Plot 2394,
 Freedom Way,
 Mufulira

DRC
 DGC AFRICA (DRC) S.A.S
 SARENS DRC S.A.S. (DRC)

T +243 89 964 9493
 T +243 89 342 9009
 T +243 89 403 1340
 E contactus@dgc-africa.com

199 Avenue Mubanzo Quartier Golf Malela,
 Commune Lubumbashi,
 Province du Haut-Katanga

MADAGASCAR
 DGC MADAGASCAR SA

T +27 (0) 82 319 8005
 T +27 (0) 79 016 9868
 T +261 32 112 2122
 E contactus@dgc-africa.com

Lot Ivx 30 Bis Ankazomanga rue Dr
 Raseta Antananarivo, 101
 Madagascar

